

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : A61K 9/10	A1	(11) International Publication Number: WO 94/03155 (43) International Publication Date: 17 February 1994 (17.02.94)
(21) International Application Number: PCT/US93/07314 (22) International Filing Date: 4 August 1993 (04.08.93) (30) Priority data: 07/927,068 7 August 1992 (07.08.92) US (71) Applicant: THE GENERAL HOSPITAL CORPORATION [US/US]; 55 Fruit Street, Boston, MA 02114 (US). (72) Inventors: WEISSLEDER, Ralph ; 197 Eighth Street, #731, Charlestown, MA 02129 (US). BOGDANOV, Alexei ; 367 Linwood Avenue, Newton, MA 02160 (US). (74) Agent: CLARK, Paul, T.; Fish & Richardson, 225 Franklin Street, Boston, MA 02110-2804 (US).		(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: HYDROGEL COMPOSITIONS AND METHODS OF USE (57) Abstract Biocompatible, biodegradable, hydrogels are prepared from a backbone bonded to a cross-linking agent. Suitable backbones include proteins and polysaccharides, e.g., albumin, polymannuronic acid, or polygalacturonic acid. Suitable cross-linking agents include polyvalent derivatives of polyethylene or polyalkylene glycol. These hydrogel compositions may be loaded with diagnostic labels, e.g., radiopaque, paramagnetic, or superparamagnetic materials, or therapeutic drugs, e.g., chemotherapeutic drugs, antibiotics, or cells that produce therapeutic agents. Such hydrogels are used for imaging, treatment, and embolization.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TG	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

- 1 -

HYDROGEL COMPOSITIONS AND METHODS OF USEBackground of the Invention

This invention relates to biocompatible and
5 biodegradable hydrogel compositions, and to methods of
use of such hydrogels for imaging during interventional
procedures of a patient.

A variety of radiologic imaging techniques are
available that allow the operator to diagnose disease and
10 monitor therapeutic interventional procedures such as
embolizations or abscess drainages. Whereas many imaging
techniques are useful for the diagnosis of disease, e.g.,
ultrasound, scintigraphy, positron emission tomography
("PET"), single photon emission computed tomography
15 ("SPECT"), X-ray, computed tomography ("CT"), and
magnetic resonance imaging ("MRI"), only X-ray
(fluoroscopy, computed tomography) and MRI are frequently
used to monitor therapeutic interventions.

Therapeutic interventional imaging procedures are
20 performed primarily in the fields of interventional
radiology ("IR") and minimal invasive therapy ("MIT").
Both fields have become important adjuncts to traditional
surgical techniques and have even replaced some classical
surgical techniques because of their lower invasiveness,
25 shorter convalescence, and similar or equal
effectiveness. Well established IR procedures include
abscess drainage, tumor embolizations, and biopsies. IR
procedures are always performed in conjunction with
radiological imaging, whereas MIT procedures are more
30 surgical in nature and use imaging only when it is
necessary to visualize the interventional devices used
during the procedure.

Therapeutic drugs are often used in conjunction
with procedures such as MIT and IR, and the concentration
35 of these drugs in a patient is indicative of the

- 2 -

efficiency of treatment. Therefore, it is important to accurately monitor the delivery, concentrations, and release, of these drugs in vivo, particularly after MIT, IR, and surgery. However, such drugs are typically not
5 detectable by conventional CT or MR imaging techniques, because they do not contain radiopaque or magnetically active labels ("contrast agents").

Contrast agents were originally developed for use with diagnostic imaging techniques to further improve the
10 diagnosis of disease. However, these agents have no therapeutic effect in interventional imaging procedures. For example, CT and MR contrast agents designed for intravascular use are water-soluble and are usually small molecules containing radiopaque, paramagnetic, or
15 superparamagnetic elements. Such contrast agents are primarily administered intravascularly to facilitate diagnosis by selectively altering the signal arising in normal or abnormal tissues. Certain contrast agents also include particulate materials for gastrointestinal (oral
20 or rectal) use. However, these gastrointestinal agents are undesirable for interventional use, because of they are hyper-osmolar and/or toxic if administered intravascularly or intracorporally.

Known diagnostic agents for human use, e.g.,
25 contrast agents for X-ray imaging, contain labels, e.g., iodine or barium, which are covalently or non-covalently bonded to other atoms to make them biocompatible. Diagnostic MR contrast agents usually contain a paramagnetic label, e.g., gadolinium ("Gd"), dysprosium,
30 iron, or manganese, or a superparamagnetic label, e.g., iron oxide. These otherwise toxic labels are made biocompatible by chelating the ions, e.g., with diethylenetriamine-pentaacetic acid ("DTPA") to form Gd-DTPA, or by coating particulates with a polymer, e.g.,
35 with dextran or arabino-galactan, to form iron oxides.

- 3 -

For example, Hall, PCT patent application 89/11874 (1990), describes contrast preparations containing a biodegradable, porous particulate substrate, e.g., Sepharose[®] or polystyrene, with surface bound
5 paramagnetic labels, e.g., Gd-DTPA, with no significant release of the label when administered. The substrate may be a hydrogel, polyglycolic acid, cross-linked protein, etc. These water-insoluble preparations may be used as MR contrast agents, e.g., for the
10 gastrointestinal tract or the vascular system.

Bligh et al., Magn. Reson. Med., 17:516-532 (1991), describes the use of soluble (e.g., dextran) and insoluble (e.g., starch or cellulose) polysaccharide-linked Gd-DTPA contrast agents for MR imaging. The
15 insoluble polysaccharides are not covalently linked to each other by a cross-linking reagent. Soluble agents were administered intravenously and insoluble agents were fed orally without injections into the blood stream.

Unger, PCT patent application 91/15713 (1991),
20 describes aqueous solutions of polymers as contrast media for MRI. These media comprise biocompatible polymers, e.g., polyethylene glycols, polyoxyethylene glycols, or polymers of galacturonic or mannuronic acid, in admixture (not covalently bound) with, e.g., paramagnetic or
25 superparamagnetic agents. If cross-linked, these contrast media may be water-insoluble.

In addition, Gd-DTPA labeled gel "tissue phantoms," i.e., artificial in vitro models of tissues, made of polyacrylamide, agarose, glutaraldehyde cross-
30 linked albumin gels, or styrenes, have been described for experimental MR imaging or other uses such as magnetic separations. However, these agents are not desirable or suitable for human use because of their local or systemic toxicity.

- 4 -

Inada et al., U.S. Patent No. 4,814,098, describes the use of a ferromagnetic material bound to a physiologically active substance, e.g., an enzyme, through a PEG derivative linker. These water-soluble colloidal solutions are used for magnetic separation of physiologically active substances.

Some radiopaque particulate materials have also been proposed for embolization purposes. These materials exhibit a strong local toxic reaction, and may elicit an immunogenic response upon repeated administration or may not be biodegradable. Furthermore, these agents do not contain paramagnetic labels and are unlikely to be useful for drug delivery estimation because of the large quantities of radiopaque materials required for CT, e.g., 10 to 40 percent of the particulate is iodine.

For example, radiopaque hylan for embolization contains a combination of hylan, e.g., hyaluronan or hyaluronate (cross-linked with vinyl-sulfone), tantalum, microcrystalline cellulose, hexamethonium chloride, and thrombin. Additional embolization materials include radiopaque non-biodegradable hydrogel microspheres based on poly (2-hydroxyethyl) methacrylate ("PHEMA")/iothalamate or iopanoic acid as described by Jayakrishnan et al., J. Biomed. Mat. Res., 25:993-1004 (1990). These microspheres were non-biodegradable over 6 month interval when implanted into rats.

Other embolization materials include Sephadex™ and Sepharose™, which are polysaccharides cross-linked with halogenated compounds such as epichlorohydrin. A method for obtaining biodegradable Sephadex, e.g., partially oxidized Sephadex, is described in Torchilin et al., J. Biomed. Mater. Res., (1977). Sephadex microparticles have also been labelled with ferromagnetic iron oxide and used for immobilizing enzymes and targeting the microparticles by applying an external magnet.

- 5 -

Certain hydrogels and microspheres have also been used for drug delivery. For example, biodegradable polymer systems have been described for the slow release of therapeutic drugs. Chemotherapeutic drugs have been
5 bound to or incorporated into a variety of slow release systems including fibrinogen microspheres, albumin, gelatin, methylene diisocyanate cross-linked collagen, polylactic acid spheres, polysaccharides such as dextran and starch, or polyamino acids. All of these agents are
10 expected to have high local tissue toxicity, be immunogenic in vivo, or be non-detectable by an imaging system.

For example, Feijen, U.S., Patent No. 5,041,292, describes a biodegradable hydrogel for drug delivery
15 systems which consists of proteins cross-linked with polysaccharides, e.g., heparin, heparan, or chondroitin, to form microspheres loaded with a drug using a solvent extraction technique.

Summary of the Invention

20 The invention features biodegradable, biocompatible, hydrogels for imaging during interventional procedures, e.g., MIT and IR, to monitor and guide these procedures. These hydrogels are water-insoluble yet water-swellaable, i.e., they can absorb
25 water. This water absorption is beneficial for MR imaging of these compounds, because this imaging technique measures the relaxivities of the protons in the water.


These hydrogels include a polymeric backbone
30 insolubilized by cross-linking agents which allow the hydrogels to absorb large amounts of water, which makes them well suited for proton relaxation imaging, e.g., MRI. The hydrogels also may be loaded with a diagnostic label detectable by CT or MR imaging techniques, and/or

- 6 -

with a therapeutic drug, and are administered intravascularly as well as by implantation. The diagnostic labels and/or therapeutic drugs can be loaded into the hydrogel during synthesis, or afterwards, e.g.,
5 by diffusion into the hydrogel compositions.

The hydrogel compositions disclosed herein have high biocompatibility, e.g., they do not cause severe side effects, and low immunogenicity of both the primary materials and their degradation products, which allows
10 repeated administration. In addition, these hydrogels when loaded with labels or drugs exhibit minimal or nonexistent local or systemic toxicity, compared to the potentially toxic labels or drugs with which they are loaded. At the same time, despite being cross-linked,
15 these hydrogels are rapidly degraded in vivo, e.g., through enzymatic degradation, into non-toxic compounds within a few days to weeks.

The invention features a biocompatible, biodegradable, hydrogel including a backbone bonded to a
20 cross-linking agent of the formula



wherein each R_1 and R_2 , independently, is an organic group, at least one of R_1 and R_2 being capable of reacting with the backbone, n is 2 or 3, preferably 2, inclusive,
25 and m is an integer from 10 to 200, and preferably from 50 to 150, inclusive. R_1 and R_2 may be the same or different.

These hydrogel compositions can be loaded with a reporter group, e.g., a diagnostic label or therapeutic
30 drug, that may be entrapped in or covalently bonded to the hydrogel. Such labels are detectable by various imaging techniques, e.g., X-ray imaging (e.g., an iodine containing compound), which includes fluoroscopy and CT

- 7 -

scanning, or magnetic resonance imaging (e.g., a gadolinium containing compound, e.g., Gd-DPTA).

The reporter group may also be a cell, or cell line, loaded into the hydrogel where the cell can grow and produce a therapeutic agent, e.g., an anti-cancer agent, antibiotic, cardiovascular agent, analgesic, central nervous system-active agent, hematopoietic agent, hemostasis agent, hormone, pro-hormone, protein, or an enzyme.

10 When the backbone includes a proteinaceous macromolecule, it includes at least 5 percent, and preferably from 20 to 50 percent, by weight of the proteinaceous macromolecule of an initial protein solution. When the backbone includes a polysaccharide
15 derivative, it includes at least 1 percent, and preferably from 2 to 5 percent, by weight of the polysaccharide derivative of an initial polysaccharide derivative solution. The backbone may also include a synthetic polymer.

20 The backbone may be a plasma protein, e.g., albumin, tissue protein, e.g., collagen, glycoprotein, recombinant protein, polyamino acid, e.g., polylysine, carboxylated polysaccharide, glycosaminoglycan, dextran derivative, starch derivative, polyethyleneimine, or
25 polyethylene glycol derivative. The backbone is preferably albumin, polymannuronic acid, or polygalacturonic acid.

 The cross-linking agent may be, e.g., a polyvalent derivative of polyalkylene glycol or polyoxyethylene
30 glycol, and is preferably a derivative of polyethylene glycol, polypropylene glycol, or copolymers thereof.

 The invention also features a method for preparing these hydrogels by reacting the backbone with the cross-linking agent to produce the hydrogel. Certain backbones
35 may first be derivatized to make them reactive, or more

- 8 -

reactive. The invention also features a method of loading the hydrogel with a reporter group, e.g., during or after synthesis of the hydrogel.

The invention further features a hydrogel for use
5 in X-ray or magnetic resonance imaging of an internal region of a patient by administering to the patient a diagnostically effective amount of a labeled hydrogel, and scanning the patient using an imaging technique that can detect the label to obtain an image of the region. A
10 "diagnostically effective amount" of the hydrogel is an amount that will provide an image of the hydrogel in the patient. The invention also features the use of such a hydrogel for the manufacture of a medicament for X-ray or magnetic resonance imaging.

15 The invention also features a hydrogel for use in diagnosing the presence of diseased tissue in a patient by X-ray or magnetic resonance imaging by administering to the patient a diagnostically effective amount of a labeled hydrogel, and scanning the patient using an
20 imaging technique that can detect the label to obtain a visible image of any diseased tissue in the patient.

In addition, the invention features a hydrogel for use in treating and imaging diseased tissue, e.g., cancer, infection, deficiency states, or hemorrhage, in a
25 patient by X-ray or magnetic resonance imaging by administering to the patient a therapeutically effective amount of a hydrogel loaded with a therapeutic drug, cell that produces a therapeutic drug, and/or label, and scanning the patient using an imaging technique that can
30 detect the label to obtain a visible image of any diseased tissue in the patient. A "therapeutically effective amount" of the hydrogel is an amount that will provide a therapeutic benefit to the patient. The treatment is effected by the release of pro-drugs,
35 therapeutic drugs, cells, proteins, etc. from the

- 9 -

hydrogel or by the hydrogel physically interrupting blood flow after intravenous administration. The invention also features a hydrogel for use in estimating the concentration of a drug delivered to a patient from a
5 hydrogel loaded with a drug and/or a label, by administering a therapeutically effective amount of the hydrogel to the patient, scanning the patient using an imaging technique that can detect the label to obtain an image of the label, calculating the release rate of the
10 label, determining a correlation between the label release rate and the concentration of the drug in the hydrogel, and estimating the concentration of the drug delivered to the patient based on the correlation.

The invention further features a hydrogel for use
15 in embolizing a given region in a patient by injecting an effective amount of a hydrogel loaded with a label and/or a drug intravascularly into the region to be embolized. The embolized region then may be scanned using an imaging technique that can detect the label to obtain an image of
20 the embolized region. The invention also features the use of such a hydrogel for the manufacture of a medicament for embolizing a given region in a patient.

Furthermore, the invention features a hydrogel for delivering a drug to a patient over an extended period of
25 time by administering a therapeutically effective amount of a hydrogel loaded with a drug, label, and/or cell to the patient.

The invention also features an interventional device, e.g., a catheter, coated with a labeled hydrogel.
30 Such a device can be imaged once inserted into an internal region of a patient in real time by coating the device with a labeled hydrogel, using the device in an internal region in the patient, and scanning the patient using an imaging technique that can detect the label to
35 obtain an image of the device.

- 10 -

The term "derivative" as used herein means a compound whose core structure is the same as or closely resembles that of a parent compound, but which has a chemical or physical modification, such as different or additional side groups; the term includes copolymers of parent compounds.

The term "loaded" when used herein to describe a hydrogel encompasses any form of incorporation (covalent or non-covalent) of the reporter group into the hydrogel of the invention. The reporter group may be entrapped within the hydrogel matrix or may be covalently bonded to either the backbone or the cross-linking agent of the hydrogel.

The term "reporter group" encompasses diagnostic labels, e.g., paramagnetic or superparamagnetic compounds such as Gd-DTPA or iron oxides, radiopaque compounds, such as iodine compounds; therapeutic drugs, such as antibiotics, hormones, anti-cancer compounds, cardiovascular agents, enzymes, analgesics, central nervous system-active drugs; and cells producing therapeutic agents, e.g., insulin.

The term "imaging" includes any technique that can diagnose disease in a human or animal patient. The term includes X-ray, CT, MR imaging, etc. The term imaging also includes practicing the technique on a patient.

Other features and advantages of the invention will be apparent from the following description of the preferred embodiments in conjunction with the claims and the drawings.

30 Brief Description of the Drawing

Figs. 1a and 1b are schematic diagrams of a hydrogel consisting of a backbone, a cross-linking agent, and at least one label. Fig. 1a shows an entrapped label, whereas Fig. 1b shows a covalently bound label.

- 11 -

Figs. 2a, 2b, and 2c are graphs showing the degradation of hydrogel compositions of the invention under varying conditions.

Fig. 3 is a graph showing the release of gadolinium and rhodamine (covalently bonded) from a hydrogel composition in an in vitro system.

Fig. 4 is a graph showing the release of gadolinium and 111-Indium (both non-covalently bonded) from a hydrogel composition in an in vitro system.

Fig. 5 is a graph showing the correlation between the release of 111-In-DTPA and Gd-DTPA from a hydrogel composition in vitro.

Fig. 6 is a graph showing the release of a therapeutic drug model (isosulfan blue) from a hydrogel composition (non-covalently bonded) in an in vitro system.

Fig. 7 is a series of MR images taken at (from left to right) 2, 5, and 10 days, of a rat implanted with a hydrogel disk (arrow), showing the release of a label over time.

Fig. 8 is a photo of the left kidney (arrow) and tumor of a rabbit which are embolized with a hydrogel composition of the invention.

Description of the Preferred Embodiments

As shown in Figs. 1a and 1b, the hydrogel compositions include a backbone (shown as $\text{---}\text{---}\text{---}$), a cross-linking agent (shown as $\bullet\text{---}\bullet$), and at least one reporter group, e.g., a label (shown as \blacktriangle). The preferred components are described separately below.

30 Backbone

The hydrogel composition includes any one of a variety of biocompatible, degradable, and metabolizable organic or inorganic backbones. The backbone is

- 12 -

preferably a hydrophilic macromolecule with multiple side groups available to react with the cross-linking agent.

The concentration of the backbone in an initial reaction solution (backbone solubilized in water) has to
5 be sufficiently high to allow extensive cross-linking and subsequent hydrogel formation. If the concentration of the backbone is too low, no hydrogel will form, although cross-linking may still occur to some extent.

Minimum concentrations for protein-based backbones
10 are typically at least 5.0% protein by weight in the reaction solution, i.e., solubilized in 95% water, but may vary for different backbones. Preferred protein hydrogels contain 20-50% protein in the initial solution.

Minimum concentrations for polysaccharide
15 backbones also depend on the structure and molecular weight of the specific backbone, but for carboxylated polysaccharides, starting solutions should be at least 1.0% of the polysaccharide. Preferred polysaccharide hydrogels contain 2-5% polysaccharide by weight in the
20 initial solution.

The following list summarizes backbones suitable for use in the present invention:

Proteinaceous backbones

- 25 Individual proteins
 - albumins
 - globulins
 - extracellular matrix proteins
(e.g. collagen, fibronectin)
 - fibrinogen
 - 30 fibrin
 - thrombin
- Plasma protein mixtures
 - plasma
 - plasma fractions
- 35 Glycoproteins
- Chemically modified proteins

- 13 -

Recombinant proteins or peptides

Sugar containing backbones

Carboxylated polysaccharides

5

polymannuronic acid
 polygalacturonic acid
 polyguluronic acid

Aminated polysaccharides
 glycosaminoglycans

10

Activated polysaccharides
 dextran derivatives
 starch derivatives

Synthetic backbones

15


Polylysines
 Polyethyleneimines
 Polyethylene glycol and its derivatives

The term "chemically modified protein" means a protein molecule in which at least one chemical bond is produced or eliminated within the molecule. The term includes proteins which are, e.g., acylated,
 20 glycosylated, deglycosylated, oxidized, reduced, fractionated into peptide fragments, or phosphorylated.

The most preferred backbones are albumin or carboxylated polysaccharides, e.g., polymannuronic or polygalacturonic acids, because of their degradation in
 25 vivo, known tissue compatibility, and relatively low cost.

Cross-linking Agents

As shown in Figs. 1a and 1b, the cross-linking agents form covalent bonds with either two backbones, one
 30 backbone, or one backbone and a reporter group. The generic formula of a hydrophilic cross-linking agent for use in the hydrogel compositions of the invention is:



- 14 -

Wherein each R_1 and R_2 , independently, is an organic group, at least one of R_1 and R_2 being capable of reacting with said backbone, n is 2 or 3, inclusive, and m is an integer from 10 to 200, inclusive. R_1 and R_2 can be the same or different organic groups. Preferably n is 2, and m is preferably from 50 to 150. These cross-linking agents are easily hydrated, decrease the toxicity of the backbone, and decrease the immunogenicity of the hydrogel compositions. The molecular structures of suitable R_1 and R_2 groups are apparent from the following list of cross-linking agents.

Preferred cross-linking agents for use in the hydrogel compositions are highly reactive, polyvalent derivatives of polyalkylene glycol (PAG). For example, when n is 2, PAG is polyethylene glycol; when n is 3, PAG is polypropylene glycol. The cross-linking agents also include copolymers of PAG, e.g., polyethylene glycol/polypropylene glycol block copolymers ("Pluronics"). As used herein, the term "polyvalent" means that the agent has two or more reactive organic groups to bind to the side groups of the hydrogel backbone, i.e., R_1 and R_2 .

The most preferred cross-linking agents are derivatives of polyethylene glycol (PEG). PEG itself is not a preferred cross-linking agent, because it will not readily react with the backbones.

Cross-linking agents suitable for use in the hydrogel compositions are summarized in the following list:

30 Polyethylene or polyoxyethylene glycol derivatives

35 bis-hydroxysuccinimide ester of PEG
bis-hydroxysulfosuccinimide ester of PEG
bis-imidate of PEG diacid
bis-imidazolidine of PEG diacid
bis-imidazolidine of PEG
bis-halide (Cl, Br, F) of PEG

- 15 -

bis-chloranhydride of PEG diacid
 bis (n-amino alkyl) of PEG
 bis (polyoxyethylene-bis[n-amino-alkyl])
 bis benzoxazolidine of PEG

5 **Polyalkylene glycol derivatives**

 bis-hydroxysuccinimide ester of PAG
 bis-hydroxysulfosuccinimide ester of PAG
 bis-imidate of PAG diacid
 bis-imidazolidine of PAG diacid
 10 bis-imidazolidine of PAG
 bis-halide (Cl, Br, F) of PAG
 bis-chloranhydride of PAG diacid
 bis (n-amino alkyl) of PAG
 bis (polyoxyalkylene-bis[n-amino-alkyl])
 15 bis benzoxazolidine of PAG

Diagnostic Labels

 The hydrogel compositions may be loaded with a
 diagnostic label either during synthesis of the hydrogel,
 or afterwards, e.g., by diffusion into the stable
 20 hydrogel composition. These labels either may be
 entrapped in the hydrogel matrix without any chemical
 bond, or they may be bonded, non-covalently or
 covalently, to the backbone or cross-linking agent of the
 hydrogel.

25 The release kinetics of the label are ultimately
 determined by the type of binding of the label and this
 invention covers the use of different release kinetics
 for different applications. For example, if fast release
 of a label is desired it should be non-covalently
 30 entrapped; when slow release is desired, e.g., when more
 toxic labels are used, the label should be covalently
 bonded.

 The following list summarizes diagnostic labels
 suitable for loading into the hydrogel compositions.
 35 This list is exemplary, and any variety of diagnostic
 label could be used. As used herein, DTPA is diethylene
 triamine-pentaacetic acid; DOTA is 1,4,7,10-
 tetraazacyclododecane-N,N,N',N''-tetraacetic acid; EDTA

- 16 -

is ethylene-diaminetetraacetic acid; DO3A is 1,4,7,10-tetraazacyclododecane-N,N',N''-triacetic acid; NOTA is 1,4,7-triazacyclononane-N,N',N''-triacetic acid; TETA is 1,4,8,11-tetraazacyclotetradecane-N,N',N'',N'''-tetraacetic acid; and HBED is hydroxybenzylethylene-diamine diacetic acid.

Radiopaque labels (for X-ray imaging)

Inorganic and organic iodine compounds
(e.g. diatrizoate, non-ionic dimers)

10 Radiopaque metals and their salts
(e.g. Ag, Au)

Other radiopaque compounds
(e.g. Ca salts, Ba salts)

Paramagnetic labels (for MR imaging)

15 Gd-DTPA and its derivatives
Gd-DTPA-protein
Gd-DTPA-poly-L-lysine
Gd-DTPA-dextran
Gd-DTPA-polymers

20 Other paramagnetic complexones
Gd complexones
(e.g. Gd-DOTA, Gd-EDTA, Gd-DO3A,
Gd-NOTA, Gd-TETA)

Mn complexones
25 (e.g. Mn-DPDP)

Fe complexones
(e.g. Fe-HBED)

Dy complexones
Cu complexones
30 Eu complexones
Er complexones
Cr complexones
Ni complexones
Co complexones

35 Superparamagnetic labels (for MR imaging)

Magnetites
Superparamagnetic iron oxides
Monocrystalline iron oxides

Other (for MR imaging)

- 17 -

Spin-labels
(e.g. nitroxyl labels)

"Complexones" are chelates of metal ions with paramagnetic properties, but greatly reduced toxicity when compared to the free metal ions.

The amount of label to be loaded into the hydrogel depends on the nature of the label. For gadolinium containing compounds, about 15 mg of Gd-DTPA-BSA/ml of hydrogel have been found to provide a clear MR image. For iodinated compounds, e.g., Hypaque™, about 100 to 400 mg of iodine/ml of hydrogel have been found to provide a clear X-ray image.

Therapeutic Drugs

A variety of therapeutic drugs also may be loaded into the hydrogel compositions of the invention, either in addition to a diagnostic label, or in place of such a label. The drugs may be loaded into the hydrogel compositions in the same way as described above for the diagnostic labels, i.e., by entrapment or chemical bonding. The following list of therapeutic drugs is exemplary, but is not intended to be exhaustive:

Chemotherapeutic agents
Antibiotic agents
Cardiovascular agents
Analgesics, CNS drugs
Drugs affecting hematopoiesis and hemostasis
Hormones, prohormones
Proteins (including albumin)
Enzymes
Cells producing therapeutic agents (e.g. insulin)
Solutes (glucose, NaCl, etc)

The rate of release, or release kinetics, of these drugs from the hydrogel compositions once administered to a patient are determined by a variety of factors including the size of the drug molecules, the specific backbone and cross-linking agents used to prepare the hydrogel, and the type of binding of the drug. This

- 18 -

invention covers the use of different drug release kinetics for different applications. For example, to achieve plasma saturation quickly, a drug may be entrapped (see Example 4, below). If slower drug release is required, covalent bonding is preferred (see Example 2, below).

The amount of drug to be loaded into the hydrogel depends on the nature of the drug. For a chemotherapeutic drug, e.g., doxorubicin, and antibiotics, e.g., gentamicin, about 10 mg of the drug/ml of hydrogel have been found to be effective. The drug loaded hydrogels are administered to patients via a catheter in amounts ranging from about 0.1 to 100 ml of the hydrogel, preferably 2 to 10 ml.

15 Biological effects

The biological effects of the hydrogel compositions in a patient depend on the manner of administration, e.g. intravascular, implantation, or intracavitary, and the type of reporter group, e.g., label or drug, incorporated into the composition. Implanted hydrogel compositions are degraded in vivo (Figs. 2a-2c) and in vitro when incubated with macrophages (not shown). In either case, as the hydrogel composition is degraded, it releases the loaded reporter group at a predetermined rate based on the known rate of degradation. These observations are confirmed by experiments which show that the preferred hydrogel compositions are degraded by proteases, such as trypsin (Fig. 2a). The degradation is a function of the amount of cross-linkage, the concentration of the backbone (see below), and the activity of the proteases.

Initial data suggest that degradation is a process which proceeds from the surface of the hydrogel particles. Cleaved fragments are presumed to be eliminated by the kidneys as is known to occur for PEG

- 19 -

fragments with molecular weights of 4,000 daltons. In addition, the reporter group may be released from the hydrogel over time even if the hydrogel is not degraded.

The tissue response to implanted hydrogel

5 compositions at the implantation sites is mild, i.e., less than that described by other investigators for wound dressings, e.g., Yoshioka, et al., Int. J. Pharm., 8:131-141 (1981). When the preferred hydrogel compositions are administered intravascularly, the protective effects of
10 PEG derivatives are believed to elicit only a minimal, if any, immunogenic response.

Use of the Hydrogel Compositions

The hydrogel compositions have a variety of medical and biomedical applications. The applications
15 and usages are described briefly below and are discussed in more detail in the following specific examples.

The compositions may be used for intravascular embolization while imaging or for chemo-embolization; for drug delivery, e.g., antibiotic delivery during abscess
20 drainages, slow release of chemotherapeutic drugs, pro-drug or enzyme delivery, and hormone replacement therapy; for estimating drug delivery by imaging based on the correlational dependence of the release of a therapeutic drug and the release of a diagnostic label; for MR
25 imaging markers without magnetic distortion, e.g., surface skin markers or intracorporal markers for radiotherapy; for coating medical devices, e.g., as a lubricious coating for catheter systems, to improve the biocompatibility of interventional devices, and to
30 visualize interventional devices with imaging techniques; for forming biodegradable devices for interventional use and implantation, e.g., a biodegradable vena cava filter with and without diagnostic labels, or a biodegradable substrate for stent or catheter synthesis; for
35 immobilizing cells in the hydrogels for injection or

- 20 -

implantation into a patient and imaging; and as a contrast agent for intravascular use.

Examples

1. Synthesis of a Bivalent Cross-linking Agent

5 Described here is the synthesis of bis(N-hydroxy-succinimidyl)polyethylene glycol disuccinate. This activated cross-linking agent is capable of reacting with amino groups of a suitable backbone.

Preparation of PEG-3350-disuccinate

10 60 g (17.9 mmol) of PEG-3,350 (Sigma Chemical Co, St. Louis, MO) was dissolved in 300 ml of dioxane in a 2-necked 1L flask and heated to 90°C. 18 g of succinic anhydride (5-fold molar excess) and 0.5 g of N,N'-dimethyl-aminopyridine were dissolved in the same
15 solution. The flask was equipped with a refluxing column and inlet for nitrogen. The mixture was slowly purged with nitrogen and heated to 100°C. for 8 hours. The mixture was cooled, concentrated three-fold by rotary evaporation, filtered on a glass-fritted filter (20-30
20 µm) to remove succinic acid, and evaporated to dryness. The residue was dissolved in a minimal amount of ethylacetate (50 ml) and added to 300 ml of ethyl ether. A precipitate formed at 4°C. and was separated, and the procedure was repeated. The thus purified precipitate
25 was dissolved in 100 ml of water and passed through a column containing 25 g of AG 50W-X8 resin (Bio-Rad, Melville, NY). The flow-through was diluted 5-fold with water and lyophilized. The yield was 50 g PEG-3350-disuccinate, or about 78%.

30 Synthesis of bis-hydroxysuccinimide ester of PEG disuccinate

30 g of the dry solid PEG-3350-disuccinate from the previous step was dissolved in 100 ml of

- 21 -

tetrahydrofuran and added to 4 g of N-hydroxysuccinimide (2-fold molar excess). After solubilization, 3.8 g (1.1 molar excess) of dicyclohexylcarbodiimide was added, the solution was stirred for 3 hours, cooled to 4°C., and
5 filtered at room temperature to remove insoluble dicyclohexylurea. The filtrate was evaporated to dryness by rotary evaporation, re-dissolved in a minimal amount of methanol (20 ml) and filtered again. Then 300 ml of diethyl ether was added and the precipitate was collected
10 by filtration. This procedure was repeated once. The yield was 23 g of bis-hydroxy-succinimide ester of PEG disuccinate, or about 72%.

2. Synthesis of Paramagnetic Cross-linked Protein Hydrogel

15 Synthesis of Gd-DTPA-albumin

Gd-DTPA was attached to bovine serum albumin (BSA) using a method similar to those previously described in Frejcarek et al., Biochem. Biophys. Res. Comm., 77:581-586 (1977) and Hnatowich et al., J. Immunol. Meth.,
20 65:147-157 (1983). Briefly, 2 g of BSA (Sigma) were dissolved in 100 ml of bicarbonate buffer at pH 9.1, and an aliquot of cyclic DTPA anhydride ("cDTPAA") (Pierce) was added. After two hours, free DTPA was removed by ultrafiltration with a YM3 filter (Amicon, Beverly, MA).
25 Transchelation of BSA-DTPA was performed with 0.1M gadolinium citrate. The reaction product, Gd-DTPA-BSA, was purified by further ultrafiltration, and then lyophilized.

Formation of a paramagnetic hydrogel

30 1400 mg BSA and 10 mg of Gd-DTPA-BSA were dissolved in 7 ml of phosphate buffered normal saline (pH 8.5). Then 460 mg of the cross-linking agent bis-hydroxysuccinimide ester of PEG disuccinate (Example 1) was dissolved in 600 μ l DMSO at 60°C. The cross-linking

- 22 -

agent was mixed with the BSA solution and reacted at room temperature for 15 minutes during which gelation occurred. Thereafter, the hydrogel composition was removed and washed in 6 L of 0.9% NaCl for 24 hours to
5 remove DMSO and unreacted products. As an alternative to BSA, equivalent amounts of human blood or human IgG were also used for cross-linking.

Formation of paramagnetic hydrogel
with a therapeutic drug

10 Five ml of a 20% BSA/Gd-DTPA-BSA solution was prepared as described above. One μ g of rhodamine X (as a model of a therapeutic drug) (Molecular Probes, Oregon) in 20 μ l DMSO was added to an 2.5 ml aliquot of this solution. One mg of doxorubicin was added to the other
15 2.5 ml aliquot. Both samples were then mixed with 230 mg of the cross-linking agent dissolved in 300 μ l DMSO, each at 60°C. After reaction at room temperature for 15 minutes, paramagnetic hydrogels with the therapeutic drug models were removed and washed in 6 L of 0.9% NaCl for 24
20 hours to remove DMSO and unreacted products. This material is preferred for embolization.

3. Synthesis of Paramagnetic Cross-linked
Polysaccharide Hydrogel

A polysaccharide-based hydrogel cross-linked with
25 a bivalent PEG derivative was synthesized as follows. A 4% sodium alginate (Sigma) solution was prepared and its pH adjusted to 5.0 using 1 N HCl. 100 mg of 15 mM of N-hydroxysulfosuccinimide (Pierce) was added while re-adjusting the pH to 5.0 to activate available carboxyl
30 groups on the polymannuronic acid backbone. 100 mg of 1-ethyl-3-(dimethyl-aminopropyl)carbodiimide hydrochloride was dissolved in 100 μ l H₂O and added to the above solution. The mixture was allowed to react for 10 minutes at room temperature. The pH of the solution
35 was then raised to 8.5 with 5 N NaOH and 100 μ l of

- 23 -

concentrated polyoxyethylene-bis (6-aminohexyl) (Sigma) or bis(polyoxyethylene-bis 3-amino-2-hydroxy-propyl) was added. After gelation, the hydrogel was dialyzed in 0.9% NaCl to remove by-products of the reaction.

5 4. Synthesis of Radiopaque Cross-linked Hydrogel

Two ml of BSA (40% with 10 mg of Gd-DTPA-BSA) was mixed with 2 ml of aqueous sodium diatrizoate 76%, which contains approximately 37% organically bound iodine. The pH was adjusted to 8.5 with bicarbonate, and reacted with
10 200 mg cross-linking agent in 200 μ l DMSO. The hydrogel was then implanted into a rat. No adverse side effects were observed.

5. Degradation of Paramagnetic Hydrogel

Hydrogels with different concentrations of albumin
15 backbone (40%, 30%, 20%, 15%, 10%) were synthesized as described in Example 2. Equivalent amounts of the hydrogel samples were then incubated at different concentrations of trypsin (0.05% = 1:1, 1:5, 1:10) (Fig. 2a), and at different temperatures (37°C., 20°C., 4°C.)
20 (Fig. 2b), to determine the degradation of the hydrogel. These experiments unequivocally demonstrate that degradation occurs in vitro and that this degradation is dependent on the activity of the protease. As shown in Fig. 2a, the highest concentration of trypsin (1:1)
25 caused the fastest degradation. Fig. 2b shows that degradation increases with temperature. Finally, Fig. 2c shows that degradation is fastest with the lowest concentration (10%) of the albumin backbone in the hydrogel composition.

30 6. Correlational Estimation of Drug Concentration

The following experiments were conducted to show that drug release kinetics from the hydrogel can be calculated by knowing the release kinetics of diagnostic,

- 24 -

e.g., radiographic, labels. The hydrogels used in these experiments were similar to those described in Example 2.

Covalent drug bonding

The hydrogel compositions contained Gd-DTPA
5 (diagnostic T1 label) and rhodamine (drug model)
covalently bound to an albumin backbone. The hydrogels
were extensively washed in saline to remove unbound
labels and then incubated with trypsin (0.05%) at 37°C.
Release of Gd (shown by □) and rhodamine (Rh_x) (shown by
10 ■) was determined by T1 and optical density measurements.
Fig. 3 compares Gd release and rhodamine release within
the first 12 hours after incubation showing excellent
correlation.

Non-covalent drug binding

15 In this set of experiments, hydrogel compositions
were prepared as described in Example 2, and T1 label
(Gd-DTPA), radioactive label (111-In-DTPA), and isosulfan
blue (therapeutic drug model), were entrapped
non-covalently in the hydrogel during synthesis. The
20 gels were subsequently incubated in normal saline. Then
T1 measurements, radioactivity measurements, and OD
measurements of the supernatant were obtained at various
time intervals. The graph in Fig. 4 summarizes the
results.

25 These data indicate that there is an excellent
correlation between the release of the model therapeutic
drug (isosulfan blue) and the diagnostic labels (111-In
or Gd). The release of either of the three compounds is
virtually identical in hydrogels of different densities.
30 For example, the best polynomial fit for two different
gels are:

20% gel: $f(x) = 24.36x - 17.87 x^2$; $r^2 = 0.999$

40% gel: $f(x) = 24.28x - 17.11 x^2$; $r^2 = 0.996$

- 25 -

As shown in Fig. 5, the correlation between release of ^{111}In -DTPA and Gd-DTPA from the hydrogel is virtually identical. From knowing one concentration, the concentration of the other label can be mathematically
5 estimated by imaging without additional physical measurements.

Drug release over time

The following experiment demonstrates the release of a non-covalently entrapped drug (modeled by isosulfan
10 blue) from a 1 ml hydrogel sample. Fig. 6 shows the exponential release of the compound.

7. MR Imaging

The following experiments were performed to determine the degradation of hydrogels after surgical
15 implantation into rats. Briefly, paramagnetic 0.5 ml hydrogels prepared as described in Example 2 were implanted into the left pararenal muscle groups (n=4), into the peritoneum (n=2), or subcutaneously (n=2) in rats (200 g CD, Charles River Breeders). The dissolution
20 of these gels, which contained covalently bonded Gd-DTPA, could be observed over time by repeated MR imaging (1.5 T GE Medical Systems, SE 300/20). These studies show that peritoneally implanted samples degraded faster (4 days) than intramuscularly implanted samples (6 days). This is
25 likely to be related to the higher concentration of peritoneal macrophages, capable of releasing proteases that enzymatically degrade the preferred hydrogels. Fig. 7 shows the dissolution of an implanted hydrogel button in a rat at 2, 5, and 10 days after implantation (from
30 left to right).

- 26 -

8. Embolization

The following embolization experiment was designed to demonstrate that the preferred hydrogel compositions of this invention can be passed through interventional catheter systems, and that these hydrogels are suitable for intravascular embolization of tumors or organs.

A 2.5 kg New Zealand White rabbit was implanted with VX2 tumor cells in the flank. Several weeks after implantation the tumor had grown to a 5 cm solid mass infiltrating the retro-peritoneum. A right femoral artery cut-down was performed and a 3Fr catheter was introduced and advanced into the aorta under fluoroscopic guidance (Fischer Imaging Systems). After injection of an iodinated contrast agent, feeding tumor vessels could be demonstrated to arise from the aorta. One of these vessels was cannulated and 0.2 ml of finely minced hydrogel beads (50-300 μ m) were administered into that tumor vessel. Subsequent fluoroscopy demonstrated complete occlusion of the tumor vessel by the hydrogel.

In addition to the above experiment, the left renal artery was cannulated and 1 ml of hydrogel was administered. Complete occlusion of the renal artery and nonperfusion of the left kidney was demonstrated by subsequent MR angiography (1.5T GE Imaging system, 3D-TOF sequence). Fig. 8 shows the results of this embolization procedure. The normally perfused right kidney (K) appears perfused (bright) after I.V. administration of a T1 agent whereas the left embolized kidney appears non-perfused (black).

9. Chemotherapeutic Drug Binding to Paramagnetic Hydrogel

A 40% solution of BSA with 10 mg BSA-Gd-DTPA in 0.1 M carbonate buffer was prepared and the pH was adjusted to 8.5. 2 mg of doxorubicin (2 mg/ml; VHA plus) was added to this solution and the pH was adjusted with

- 27 -

0.05 M HEPES buffer. 200 mg of cross-linking agent (see Example 1) was added and dissolved in 200 μ l of DMSO. The sample was polymerized at room temperature for 2 hours and then dialyzed in 0.9% NaCl for 24 hours.

5 Binding of doxorubicin to the hydrogel matrix was greater than 95%.

10. Color coding

To easily recognize an entrapped or covalently bonded reporter group within a hydrogel, a chromophore, 10 or mixtures of chromophores, may be added to the hydrogel during synthesis. A variety of chromophores are suitable including, e.g., indocyanine green, fluorescein, rhodamine, rose bengal, gentian violet, methylene blue, isosulfan blue, and other reactive colors (Sigma).

15 In the following example, a Gd-DTPA containing hydrogel was synthesized as described in Example 2. Briefly, a solution containing BSA and BSA-Gd-DTPA was reacted with 10 μ l of DMSO to which had been added 5 μ g of rhodamine X (Molecular Probes, Oregon). The solutions 20 were reacted at room temperature for 15 minutes, cross-linked with activated PEG, and then washed to remove free rhodamine.

11. Lyophilization

Hydrogel prepared as described in Example 2 was 25 subjected to lyophilization (Vitis Freezemobile) by first freezing the sample in liquid nitrogen. Lyophilized hydrogel samples were stored for two months and reconstituted with water to yield a hydrogel with properties similar in appearance, density and magnetic 30 properties, to that of the non-lyophilized hydrogel.

- 28 -

12. Use of the Hydrogels as Contrast Agents Without Embolization

The hydrogel composition described in Example 2 was finely homogenized (Brinkman Polytron, Wheaton tissue homogenizer, Branson sonifier) to obtain an average particle size of below 100 nm. The size of the particles was controlled by passing the solution successively through 0.45 and 0.1 μm filters (Acrodisk). After concentration by centrifugation, 1 ml of the suspension was administered intravenously to a rat. Because the individual particles are too small to occlude capillaries, no embolization occurred and the animal survived the injection.

13. Coating of Interventional Devices with Paramagnetic Hydrogel

In the following experiment, an angiographic catheter was coated with a paramagnetic hydrogel for improved delineation by MR imaging. The surface of a 3 Fr angiographic catheter was cleaned with glass wool and ether. A section of the catheter was then submerged in a 20% BSA-(Gd-DTPA) solution (200 μl). The albumin adhered to the catheter non-specifically. The catheter was then dried at room temperature and subsequently immersed in 50 μg of DMSO solution containing the hydroxysuccinimide ester of PEG-bis-succinate of Example 1 to cross-link the albumin on the catheter. The catheter was then washed in saline and is ready for MR imaging.

14. Hydrogel Matrix for Cell Support

Living cells may be loaded into the hydrogel compositions and propagated to produce therapeutic agents. Such cells would have low or non-existent toxicity. For example, cells with the capacity to secrete therapeutic agents, e.g., insulin or other hormones, enzymes, or proteins, can be loaded into a

- 29 -

hydrogel and implanted into a patient. If an appropriate label is also loaded into this hydrogel, an MR image will indicate cell density and activity, and/or the presence or concentration of the therapeutic agents, in the
5 hydrogel.

To prepare such a hydrogel composition, the desired cells are dispersed, e.g., by vortexing, in a sterile solution of 10% serum, e.g., fetal calf, bovine, or human, in Dulbecco's modified Eagle medium at a pH of
10 7.9. At this stage, suitable therapeutic drugs and/or diagnostic labels as described above may be added. The number of cells loaded into the hydrogel is selected to achieve a specific dosage of the therapeutic agent secreted by the cells per day. For example, if the cells
15 are secreting insulin, the standard dosage is about 10 to 80 I.U./day. This mixture is cross-linked by adding a cross-linking agent, e.g., the bis(N-hydroxy-succinimidyl)polyethylene glycol disuccinate described in Example 1, which is dissolved in DMSO. The cell loaded
20 hydrogel is kept in tissue culture medium for a time sufficient to remove any DMSO or other contaminants, e.g., 12 to 24 hours, before implantation into a patient.

Other Embodiments

It is to be understood that while the invention
25 has been described in conjunction with the preferred embodiments thereof, that the foregoing description is intended to illustrate and not limit the scope of the invention, which is defined by the scope of the appended claims. Other aspects, advantages, and modifications
30 within the scope of the invention will be apparent to those skilled in the art to which the invention pertains.

What is claimed is:

- 30 -

Claims

1. A biocompatible, biodegradable, hydrogel comprising a backbone bonded to a cross-linking agent of the formula



wherein each R_1 and R_2 , independently, is an organic group, at least one of R_1 and R_2 being capable of reacting with said backbone, n is 2 or 3, inclusive, and m is an integer from 10 to 200, inclusive.

10 2. The hydrogel of claim 1, further comprising a reporter group loaded into said hydrogel.

3. The hydrogel of claim 2, wherein said reporter group is entrapped in said hydrogel.

15 4. The hydrogel of claim 2, wherein said reporter group is covalently bonded to said hydrogel.

5. The hydrogel of claim 1, wherein said backbone comprises a proteinaceous macromolecule.

20 6. The hydrogel of claim 5, wherein said backbone comprises at least 5 percent protein by weight of an initial proteinaceous solution.

7. The hydrogel of claim 6, wherein said backbone comprises from 20 to 50 percent protein by weight of said initial solution.

25 8. The hydrogel of claim 1, wherein said backbone comprises a polysaccharide derivative.

- 31 -

9. The hydrogel of claim 8, wherein said backbone comprises at least 1 percent polysaccharide derivative by weight of an initial polysaccharide derivative solution.

10. The hydrogel of claim 9, wherein said backbone comprises from 2 to 5 percent polysaccharide derivative by weight of said initial solution.

11. The hydrogel of claim 1, wherein said backbone comprises a synthetic polymer.

12. The hydrogel of claim 1, wherein said backbone is a plasma protein, tissue protein, glycoprotein, recombinant protein, polyamino acid, carboxylated polysaccharide, glycosaminoglycan, dextran derivative, starch derivative, polyethyleneimine, or polyethylene glycol derivative.

13. The hydrogel of claim 12, wherein said backbone is albumin, polymannuronic acid, or polygalacturonic acid.

14. The hydrogel of claim 1, wherein m is an integer from 50 to 150, inclusive.

15. The hydrogel of claim 1, wherein R_1 and R_2 are each the same.

16. The hydrogel of claim 1, wherein R_1 and R_2 are different.

17. The hydrogel of claim 1, wherein said cross-linking agent is a polyvalent derivative of polyalkylene glycol or polyoxyethylene glycol.

- 32 -

18. The hydrogel of claim 17, wherein said cross-linking agent is a derivative of polyethylene glycol, polypropylene glycol, or copolymers thereof.

19. The hydrogel of claim 17, wherein said cross-
5 linking agent is a bis-hydroxysuccinimide ester of polyethylene glycol ("PEG"), bis-hydroxysulfosuccinimide ester of PEG, bis-imidate of PEG diacid, bis-imidazolidine of PEG diacid, bis-imidazolidine of PEG, bis-halide of PEG, bis-chloranhydride of PEG diacid, bis (n-amino alkyl) of
10 PEG, bis (polyoxyethylene-bis [n-amino-alkyl]), bis benzoxazolidine of PEG, bis-hydroxysuccinimide ester of polyalkylene glycol ("PAG"), bis-hydroxysulfosuccinimide ester of PAG, bis-imidate of PAG diacid, bis-imidazolidine of PAG diacid, bis-imidazolidine of PAG, bis-halide of PAG,
15 bis-chloranhydride of PAG diacid, bis (n-amino alkyl) of PAG, bis (polyoxyalkylene-bis [n-amino-alkyl]), or bis benzoxazolidine of PAG.

20. The hydrogel of claim 2, wherein said reporter group comprises a diagnostic label.

20 21. The hydrogel of claim 20, wherein said label is detectable by X-ray, or magnetic resonance imaging.

22. The hydrogel of claim 21, wherein said X-ray detectable label is an iodine containing compound.

23. The hydrogel of claim 21, wherein said
25 magnetic resonance imaging detectable label is a gadolinium containing compound.

24. The hydrogel of claim 23, wherein said label is gadolinium-diethylenetriamine-pentaacetic acid.

- 33 -

25. The hydrogel of claim 2, wherein said reporter group comprises a drug.

26. The hydrogel of claim 20, wherein said reporter group further comprises a drug.

5 27. The hydrogel of claim 25, wherein said drug is an anti-cancer agent, antibiotic, cardiovascular agent, analgesic, central nervous system-active agent, hematopoietic agent, hemostasis agent, hormone, pro-hormone, protein, or an enzyme.

10 28. The hydrogel of claim 2, wherein said reporter group comprises a cell loaded into said hydrogel.

 29. The hydrogel of claim 20, wherein said reporter group further comprises a cell loaded into said
15 hydrogel.

 30. The hydrogel of claim 29, wherein said cell grows in said hydrogel and produces a therapeutic agent.

 31. The hydrogel of claim 30, wherein said therapeutic agent is an anti-cancer agent, antibiotic,
20 cardiovascular agent, analgesic, central nervous system-active agent, hematopoietic agent, hemostasis agent, hormone, pro-hormone, protein, or an enzyme.

 32. The hydrogel of claim 31, wherein said therapeutic agent is insulin.

25 33. A method for preparing the hydrogel of claim 1 comprising reacting said backbone with said cross-linking agent to produce said hydrogel.

- 34 -

34. The method of claim 33, further comprising derivatizing said backbone.

35. The method of claim 33, further comprising loading said hydrogel with a reporter group.

5 36. The method of claim 35, wherein said reporter group is loaded into said hydrogel during synthesis of said hydrogel.

37. The method of claim 35, wherein said reporter group is loaded into said hydrogel after synthesis of
10 said hydrogel.

38. The hydrogel of claim 20 for use in X-ray or magnetic resonance imaging of an internal region of a patient.

39. The hydrogel of claim 20 for use in
15 diagnosing the presence of diseased tissue in a patient by X-ray or magnetic resonance imaging.

40. The use of the hydrogel of claim 20 for the manufacture of a medicament for X-ray or magnetic resonance imaging.

20 41. The hydrogel of claim 26 or 30 for use in treating and imaging diseased tissue in a patient by X-ray or magnetic resonance imaging.

42. The hydrogel of claim 26 for use in estimating the concentration of a drug delivered to a
25 patient from said hydrogel by administering a therapeutically effective amount of said hydrogel to the patient, scanning the patient using an imaging technique

- 35 -

that can detect said label to obtain an image of said label, calculating the release rate of said label, determining a correlation between the label release rate and the concentration of said drug in said hydrogel, and
5 estimating the concentration of said drug delivered to the patient based on said correlation.

43. The hydrogel of claim 1 or 26 for use in embolizing a given region in a patient.

44. The hydrogel of claim 43, which is further
10 used for scanning the patient using an imaging technique that can detect said label to obtain an image of the embolized region.

45. The use of the hydrogel of claim 1 or 26 for the manufacture of a medicament for embolizing a given
15 region in a patient.

46. The hydrogel of claim 25 or 30 for delivering a drug to a patient over an extended period of time.

47. A device for use in therapeutic interventional procedures, comprising an interventional
20 device coated with the hydrogel of claim 20.

FIG. 1a




FIG. 1b




FIG. 2a




FIG. 2b






FIG. 2c**FIG. 3**



FIG. 4**FIG. 5**


FIG. 6

FIG. 7



FIG. 8



INTERNATIONAL SEARCH REPORT

1. national application No.
PCT/US93/07314

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) :A61K 9/10

US CL :424/426

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : . 424/426, 484; 252/315.1

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 5,041,292 (FEIJEN) 20 AUGUST 1991, SEE ABSTRACT.	1-47
A	US, A, 4,814,098 (INADA) 21 MARCH 1989, SEE ABSTRACT.	1-47

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be part of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L documents which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*G*	document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means		
P document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

05 OCTOBER 1993

Date of mailing of the international search report

16 DEC 1993

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. NOT APPLICABLE

Authorized officer

EDWARD WEBMAN

Telephone No. (703) 308-2351